

## Techno Plug

---

### Rapid setting cement-based, water-stopping mortar

#### Uses

For the rapid temporary patching and plugging of concrete segments, concrete and brick tunnel linings, sewage systems, below ground access chambers, pipes, basements, foundations and mines.

#### Advantages

- Emergency water-stopping capability
- Single component - only the addition of clean water is required
- Excellent bond to the substrate
- Low exotherm, minimizes thermal cracking
- Pre-bagged formulation to overcome variations in site batching
- Contains no chloride admixtures

#### Description

Techno Plug is supplied as a ready to use blend of dry powders which requires only the site addition of clean water to produce a highly consistent, rapid setting mortar which is easy to apply in many difficult conditions. The material is based on a blend of cements, graded aggregates, special fillers and chemical additives which control the rate of set and minimize the risk of thermal cracking. Techno Plug provides an initial set time of approximately one minute.

#### Design criteria

Techno Plug can be applied to horizontal, vertical or overhead surfaces at a wide range of thicknesses. Generally, the volume of mixed material used in a single application is restricted to that which can be applied by trowel or gloved hand. Thicker sections can be built up in layers.

#### Properties

Compressive strength (BS6319Pt2:1983)	: 5 N/mm <sup>2</sup> @ 2 hours @ 20°C 25 N/mm <sup>2</sup> @ 28 days @ 20°C
Initial set time	Approximately 1 min @ 20°C

Note: Set times will be extended when mixed at lower temperatures.

#### Specification

##### Water stopping mortar

The water stopping mortar shall be Techno Plug a single component cement-based blend of powders to which only the site-addition of clean water shall be permitted. It must be chloride-free and must be formulated to prevent high exotherm and minimize thermal cracking.

#### Instructions for use

---

Modern Technologies for Construction Chemicals

Factory: Wadi Elnatroun - First Industrial Area.  
Head Office: New Maadi - 3\288 St. from Aljazaer St.  
Fax. & Tel.: 02-25200833      Mob. : 010 209 65554  
[www.mtcchem.com](http://www.mtcchem.com)

### **Preparation**

Areas to be patched should be cut back to a depth of 15 mm and given a good mechanical key. Feather-edges must not be allowed. Surface should be brushed clean to remove loose material, dust and laitance. Grease, slime or mould growth should be removed by steam cleaning or high-pressure water jetting. A proprietary degreasing agent should be used for removal of light oil or grease contamination.

To seal leaks, crack openings must be chased out to approximately 20 mm square. The chase should always be undercut to avoid leaving a v-section. All loose material and debris should be removed.

### **Mixing**

Techno Plug should be added to clean water in the following

#### **proportions:**

one part clean water: 3 parts Techno Plug (measured by Volume). Mix to a stiff consistency in a suitable mixing drum or bucket, using a trowel or gloved hand. Due to the rapid set characteristics of the product, only prepare a quantity of mortar which can be placed within the prescribed set time.

### **Application**

Trowel apply or hand-knead the mixed mortar in place, ensuring maximum contact with the substrate before the material sets. If being used to plug running water, Techno Plug should be used and held in place until the initial set is reached.

**Note:** the minimum applied thickness of Techno Plug should be 15 mm.

#### *Low temperature working*

In cold conditions down to 1°C, the use of warm water (up to 20°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should be adopted. The material should not be applied when the substrate and/or air temperature is 1°C and falling. At 1°C static temperature or at 1°C and rising, the application may proceed.

#### *High temperature working*

at ambient temperatures above 35°C, the material should be stored in the shade and cooler water (down to 20 °Q used for mixing).

### **Cleaning**

Techno Plug products should be removed from tools, equipment and mixers with clean water prior to the initial set. Cured material can only be removed mechanically.

### **Limitations**

#### **Storage**

#### **Shelf life**

Techno Plug has a shelf life of 6 months if kept in a dry store in the original, unopened bags or packs. If stored at high temperatures and/a high humidity conditions the shelf life will be reduced.

---

Modern Technologies for Construction Chemicals

**Factory: Wadi Elnatroun - First Industrial Area.**  
**Head Office: New Maadi - 3\288 St. from Aljazaer St.**  
**Fax. & Tel.: 02-25200833      Mob. : 010 209 65554**  
[www.mtcchem.com](http://www.mtcchem.com)

## Precautions

### Health and safety

Techno Plug products contain cement powders which, when nixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes.

Wear suitable protective clothing gloves, eye protection and respiratory protective equipment. The use of barrier creams provides additional skin protection.

In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Techno Plug should not be used when the temperature is In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately.

–

### Estimating

#### Supply

---

Techno Plug	:	6 kg bags
-------------	---	-----------

---

#### Yield

---

Techno Plug	:	5 liters per 10 kg bag
-------------	---	------------------------

---

### Technical support

M.T.C. offers a comprehensive technical support service to for specifies, end users and contractors. It is also able to offer Data Sheet, on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

### Fire

Techno Plug is non-flammable.