

Techno Flow 110 Ls

Well graded plasticized admixture expanding grout admixture for the injection of soil cracks.

Uses

As an admixture for cementations grouts where a low water/cement ratio and positive expansion are required. Application includes bed grouting, duct grouting, non-shrink infilling and jointing. Specially formulated for grouting precast cables ducts, used mainly for the injection of soil cracks and bricks cracks.

Advantages

Shrinkage compensation Gaseous expansion system compensates for plastic shrinkage and settlement in cementations grouts.

Durability Reduced water/cement ratio ensures low permeability and long-term performance in service.

Flow ability Gives high grout fluidity with low water/cement ratio, for ease of placement or injection.

Iron-free No metallic iron content to corrode and cause staining or deterioration due to rust expansion in the grout.

Chloride-free Composition allows high early strength development in grouts, without the use of chlorides.

Specially formulated for grouting precast cables ducts.

Description

Techno Flow 110 Ls is supplied as a powder admixture for cementations grouts and concrete. The material is a combination of a plasticizing agent and a gas producing expansion medium. The plasticizing agent allows the use of a low water/cement ratio with consequent high strengths and durability. The expansive medium counteracts the natural settlement and plastic shrinkage of the grout and aids stability and cohesion. Sufficient restrained expansion is developed to ensure a high degree of interfacial contact. If repacked cement based grout is required instead of an admixture, use Techno Flow range, which only requires the addition of water.

Specification clauses

Performance specification

All grouting (specify details and areas of application) must be carried out with a cement-based grout incorporating a plasticized, expanding powder admixture. The admixture must be iron-free and chloride-free and shall be added to the grout in the proportions 225 gm of admixture per 50 Kg of cement. The admixture shall provide an expansion of 1 - 4% in the plastic grout, by means of a gaseous system. The admixture must be stored, handled and placed strictly in accordance with the manufacturer's instructions.

Properties

Chloride content Nil

Setting times

Techno Flow 110 Ls does not significantly affect the setting times of cement-based grouts.

Modern Technologies for Construction Chemicals

Factory: Wadi Elnatroun - First Industrial Area.
Head Office: New Maadi - 3\288 St. from Aljazaer St.
Fax. & Tel.: 02-25200833 Mob. : 010 209 65554
www.mtcchem.com

Expansion characteristics

The controlled positive expansion in unset grouts Incorporating Techno Flow 110 Ls overcomes plastic settlement when measured in accordance with ASTM C827. An unrestrained expansion of 1-4% is typical.

Time of expansion

15mins to 4 hours. Temperatures above 20 °C may slightly reduce these times.

Pressure to restrain plastic expansion

Approximately 0.004 N/mm².

Compatibility

Techno Flow 110 Ls is compatible with all types of Portland cement but is incompatible with High Alumina Cement. Techno Flow 100 may be used in mixes containing certain Other M.T. C. admixtures M. T. C. technical department should be consulted in these situations.

Instructions for use**Dosage****Typical mixes**

5kg of Techno Flow 110 Ls per 50 Kg cement.

Overdosing

Drastic overdosing of Techno Flow 110 Ls increases expansion and may cause frothing.

Mixing

For best results a mechanically powered grout mixer must be used. For quantities up to 50 Kg a slow speed drill fitted with a high shear paddle is suitable. The selected water content should be accurately measured into the mixer. Slowly add the cement (and sand if required) and Techno Flow 110 Ls. Mix continuously for 5 minutes, making sure that a smooth even consistency is obtained.

Application

Areas to be grouted should be prepared in the usual way to ensure, clean sound, pre-wetted substrates. Place the grout within 20 minutes of mixing to gain the full benefit of the expansion process. Adopt usual placing or pumping procedures ensuring a continuous operation.

Curing

On completion of the grouting operation, exposed areas which are not to be cut back should be thoroughly cured by means of water application. Techno Cure curing membrane or wet Hessian.

Cleaning

Grouts mixed with Techno Flow 110 Ls should be removed from tools and equipment immediately after use with clean water. Remove cured material mechanically

Precautions**Health and safety**

When mixing grouts with Techno Flow 110 Ls. Gloves should be worn. Splashes of grout to the skin or eyes should be washed off with clean water. In the case of prolonged irritation, seek medical advice.

Fire

Modern Technologies for Construction Chemicals

Factory: Wadi Elnatroun - First Industrial Area.
Head Office: New Maadi - 3\288 St. from Aljazaer St.
Fax. & Tel.: 02-25200833 Mob. : 010 209 65554
www.mtcchem.com

Techno Flow 110 Ls is non-flammable.

Storage

Techno Flow 100 has a shelf life of 12 months if Kept in a dry store in its original packaging .High temperature and humidity storage may reduce this.

Packaging

Techno Flow 110 Ls is supplied in 5 Kg units. Other forms of packaging may be available for special orders.

Supply

Contact your local M. T. C. office or representative.

Technical service

The company provides a technical advisory service supported by a team of specialists in the field.