

Techno Mix Sp 723

Workability retention, high range water reducer and super plasticizer

Uses

Gives increased working life to fresh concrete. Increases workability without extra water, reducing placing time and costs. Improves cohesion, minimizing segregation and improving surface finish. Aids pumping by improving cohesion and reducing workability loss. Allows a reduction in water/cement ratio, enhancing durability by producing low permeability concrete with reduced shrinkage cracking potential. Chloride free, safe for use in prestressed and reinforced concrete. Can be used with concrete containing micro silica and other cement replacements

Standards compliance

Techno mix sp 723 complies with BS 5075 part 3 and ASTM C494 as Type G.

Description

Techno mix sp 723 is a chloride free workability retention admixture based on selected organic polymers. It is supplied as a brown solution, which instantly disperses in water. Techno mix sp 723 disperses the fine particles in the concrete mix enabling the water content of the concrete to perform more effectively. The increased workability, cohesion and retardation minimize loss of workability.

Technical Support

M.T.C provides a technical advice on mix design, admixture selection, and evaluation trials

Dosage

The optimum dosage of Techno mix sp 723 to meet specific requirement should always be determined by trials using the normal dosage range is 0.6 to 1.5 litres/100 kg of cementitious material, including PFA, GGBFS and micro silica.

Use at other dosages, Dosages outside the typical range quoted above may be used if necessary and suitable to meet particular mix requirements. Contact M. T. C for advice in these cases.

Properties

Appearance	brown, liquid
Specific gravity	1.7 to 1.19 at 20°C
Chloride content	Nil to BS 5075

Instructions for use

Mix design for workability retention The mix design should be one suitable for use as a pump mix. To obtain the best results for workability retention, the initial workability should be above 150 mm slump. The retardation and improved cohesion provided by Techno mix sp 723 then act to enhance the workability retention characteristics.

Advice on mix design for flowing concrete is available from M.T.C In correctly designed flowing, the improved dispersion of the cement particles and the more efficient use of mixing water will improve mix cohesion.

The improved cohesion obtained with Techno mix sp 723 will also help to minimize bleed and segregation. After initial trials, minor modifications to the mix design may be made to optimize

Modern Technologies for Construction Chemicals

Factory: Wadi Elnatroun – First Industrial Area.
Head Office: New Maadi – 3\288 St. from Aljazeera St.
Fax. & Tel.: 02-25200833 Mob. : 010 209 65554
www.mtcchem.com

performance

Compatibility

Techno mix sp 723 is compatible with other M. T. C admixtures used in the same concrete mix. All admixtures should be added to the concrete separately and must not be mixed together prior to addition. The resultant properties of concrete containing more than one admixture should be assessed by the trial mixes. Techno mix sp 723 is suitable for use with all types of ordinary Portland cements and cement replacement materials such as PFA, GGBFS and micro silica.

Dispensing

The correct quantity of Techno mix sp 723 should be measured by means of a recommended dispenser. Normally, the admixture should be added to the concrete with the mixing water to obtain the best Results.

Effects of overdosing

An overdose of double the amount of Techno mix sp 723 will result in a significant increase in retardation as compared to that normally obtained. Provided that adequate curing is maintained, the ultimate strength of the concrete will not be impaired by increased retardation and will generally be increased.

The effects of overdosing will be further increased if sulphate resisting cement or cement replacement materials are used. Over dosage is also likely to cause increased air entrapment, which will tend to reduce strength. The degree of this effect will depend on the particular mix design and overdose level.

Packaging

Techno mix sp 723 is available in drum and bulk Supply.

Storage

Techno mix sp 723 has a minimum shelf of 12 months provided the temperature is kept within the range of 2° C to 50° C.

Precautions

Health and safety

Techno mix sp 723 does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes. Suitable protective gloves and goggles should be worn. Splashes on the skin should be removed with water. In case of contact with eyes, rise immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

Fire

Techno mix sp 723 is water based and non- flammable.

Cleaning and disposal

Spillages of Techno mix sp 723 should be absorbed onto sand, earth or vermiculite and transferred to suitable containers.

Modern Technologies for Construction Chemicals

Factory: Wadi Elnatroun – First Industrial Area.
Head Office: New Maadi – 3\288 St. from Aljazaer St.
Fax. & Tel.: 02-25200833 Mob. : 010 209 65554
www.mtcchem.com